


CARBON RAISER



Physical & chemical properties

Item	Fixed Carbon	Sulphur	Ash	Volatile matter	Nitrogen	Moisture	Size(mm)
GPC	99% min.	0.03% max.	0.3% max.	0.5% max.	0.01% max.	0.3% max.	1-3
GPC	99% min.	0.03% max.	0.3% max.	0.8% max.	0.03% max.	0.3% max	1-5
GPC	99% min.	0.03% max	0.3% max.	0.5% max.	0.01% max.	0.3% max.	2-5
GPC	98% min	0.07% max.	1% max.	1% max.	0.03% max.	0.5% max	0.2-1
GPC	98% min	0.1% max.	1% max.	1% max.	0.05%max.	0.5% max.	0-0.5
Special grain size can be customized based on your actual requirement.							

Item	Fixed Carbon	Sulphur	Ash	Volatile matter	Real density g/cm	Electric resistance	Moisture	Size(mm)
CPC	98.5% min.	3% max.	0.5% max.	0.7% max.	2.05% min.	500 max.	0.5% max.	0-2
CPC	98.5% min.	3% max.	0.5% max.	0.7% max.	2.05% min.	520 max.	0.5% max.	0.5-2
CPC	98.5% min.	1.5% max.	0.5% max.	0.7% max.	2.05% min.	520 max.	0.5% max.	1-5
CPC	98.5% min.	1.0% max.	0.5% max.	0.7% max.	2.05% min.	520 max.	0.5% max.	1-8
CPC	98.5% min.	1.6% max.	0.5% max.	0.7% max.	2.05% min.	520 max.	0.5% max.	2-8
Special grain size can be customized based on your actual requirement.								

Product Packing

- 1. In 25kgs per bag
- 2. 25kgs bags put into a 1000kg jumbo bag
- 3. In 1000kg jumbo bag

Q&A

- 1. Port: Tianjin Port
- 2. Packing: Woven Bag
- 3. Delivery time: 5-7days
- 2. Minimum order quantity: 20tons
- 3. Supply Ability: 5000 tons/month