

CENTER INTERNATIONAL GROUP COMPANY LIMITED

TEST REPORT

SCOPE OF WORK

GLASS WOOL BLANKET

REPORT NUMBER

201231012SHF-001

TEST DATE(S)

2021-01-19 - 2021-01-26

ISSUE DATE

2021-01-26

PAGES


5

DOCUMENT CONTROL NUMBER

LFT-APAC-SHF-OP-10k(May 1, 2020)

© 2020 INTERTEK

Intertek Testing Services Shenzhen Ltd. Shanghai Fengxian Branch



Test Report

Statement

- 1.This report is invalid without company's special seal for testing on assigned page.
- 2.This report is invalid without authorized person's signature.
- 3.This report is invalid where any unauthorized modification indicated.
- 4.Don't copy this report in partial (except full copy) without any official approval in written by our company. This report is invalid without re-stamping the special seal for testing in copying report.
- 5.Any holder of this document is advised that this report is for the exclusive use of Intertek's Customer and is provided pursuant to the agreement between Intertek and its Customer. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. This report was made with due care within the limitation of a defined scope of work and on the basis of information, materials and instructions received from the Customer or its nominated third parties. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. The tests results are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results.
- 6.Intertek's written consent is required to use Intertek's name or logo on the object, product or service being tested. The observations and test results in this report relate only to the sample under test. This report alone does not indicate that the item, product or service has passed any Intertek certification program.
- 7.The report was digital signed by Shang Hai, Intertek Group plc, please using Adobe Acrobat Reader to verify the authenticity.



Test Report

Issue Date: 2021-01-26 Intertek Report No. 201231012SHF-001
Applicant: CENTER INTERNATIONAL GROUP COMPANY LIMITED
Address: Center Shixing Group Co., Ltd., No. 1, Rongxing North Second Street, Beijing Economic and Technological Development Zone
Attn: Xiaohan Zhang
Manufacturer : HEBEI GUO ME NEW-TYPEBUILDING MATERIAL COMPANY LTD
Address : Area C, Guome, Zhuangquan Village Industrial Park, Liuge, Dacheng County, Langfang City
Test Type : Performance test, samples provided by the applicant.

Product Information

Product Name	GLASS WOOL BLANKET	Brand	/
Sample Description	Good Condition	Sample Amount	2 rolls
		Received Date	2021-01-14
Sample ID	Model	Specification	
S201231012SHF.007	UET GB 0221	18k	

Test Methods And Standards

Test Standard	ASTM E84-20
Specification Standard	/
Test Conclusion	The samples were tested according to the above standards, and the results are shown in the following page.

Note:

1.This report relates specifically to the sample(s) that were drawn and provided by the applicant or their nominated third party. The reported result(s) provide no warranty or verification on the sample(s) representing any specific goods and/or shipment and only relate to the sample(s) as received and tested.

Report Authorized


 
Name: Harrison Li Name: Jackie Zhou
Title: Reviewer Title: Project Engineer

Test Report

Issue Date: 2021-01-26

Intertek Report No. 201231012SHF-001

Test Items, Method and Results:

Test Method: ASTM E84-20 Standard Test Method for Surface Burning Characteristics of Building Materials

Specimen Mounting Method:

The 24.02-ft. long test specimen consisted of two 9.84-ft. long x 23.62-in. wide x 2.95-in. thick and one 4.33-ft. long x 23.62-in. wide x 2.95-in. thick "GLASS WOOL BLANKET".

The exposed side for fire was the fluffy side.

The specimen was supported with 0.25-in. diameter metal rods that were spaced approximately every two feet.


Test Observation (min:sec)

Melting	Blistering	Transient Ignition	Steady Ignition	Flaming drops
6:51	/	/	/	/
Delamination	Sagging	Shrinkage	Falling	Floor Flame
/	7:03	/	/	/


Test Result

Flame Spread Index (FSI)	0	Smoke Developed Index(SDI)	0
--------------------------	---	----------------------------	---

Flame spread graph



Smoke developed graph



Test Report

Issue Date: 2021-01-26

Intertek Report No. 201231012SHF-001

Appendix A: Sample Received Photo



Revision:

NO.	Date	Changes	Author	Reviewer
201231012SHF-001	2021-01-26	First issue	Jackie Zhou	Harrison Li